Re Alloys Sp. z o.o. Cieszyńska 23 43-170 Łaziska Górne tel./fax +48 32 324 71 06 NIP 629 21 35 648 REGON 276099119 biuro@realloys.pl www.realloys.pl

Sąd Rejonowy Katowice Wschód w Katowicach Wydział VIII Gospodarczy KRS Nr KRS 0000027895 Kapitał Zakładowy 13.564.500,00 zł

TECHNICAL DATA SHEET SILIMIC

Date of formation / date of updating: 02.01.2013 / 21.03.2018

1. Description

SILIMIC is dry silica fume /microsilica, amorphous silica, amorphous silica dioxide/, available in two main forms:

UNDENSIFIED – SILIMIC U; with a typical bulk density of till 350 kg/m³

DENSIFIED - SILIMIC D; with a typical bulk density of 450-650 kg/m³

The parameter of Bulk density set on Producer's production line is not repetable. The transport and storage can change them.

CAS: 69012-64-2 EINECS: 273-761-1

REACH: 01-2119486866-17-0024

2. Application

Additive (mineral admixture) in manufacturing of; (ready mix) high-strength concrete, repair products as mortars and grouts, shotcrete, manufacturing of sealants and adhesives, component of refractories.

Additive in other building materials such as roof tiles and facade cladding.

3. Storage

SILIMIC should be kept in dry storage. Subjected to moisture and allowed to dry again may result in inferior performance. Not store in temperature near to or below 0 degrees of Celsius. Keep away from hydrofluoric acid (HF).

4. Use by date

Use by date, indefinite. Provided that conditions specified in point 3 are fullfield Silimic parameters remain unchanged.

5. Typical Chemical and Physical Characteristics

SiO2 (% by weight of dry mass) - min 90 %, Specific surface (m^2/g) - 15 - 35, Pozz. Activity Index - min 100 %, Retained on 45 micron sieve - max 1%. Bulk density - Undensifeid - till 350 kg/m³ Bulk density - Densifeid - 450 - 650 kg/m³

6. Packing

SILIMIC is supplied in a range of packing:

- bulk in road tanker,
- 20 kg paper bags,
- Big bags with a capasity of 1 m³ or 1,6 m³

7. Quality Control and Compliance

Re Alloys Sp. z o.o. is certified according to EN ISO 9001

The chemical composition and physical properties are regularly tested, SILIMIC meets the requirements of the EN 13263 from the European Committee for Standarization.

The information given on this datasheet is accurate to the best knowledge Re Alloys. The information is offered without guarantee, and Re Alloys accept no liability for any direct or indirect damage from its use. The information is subject to change without notice. For latest update or futher information or assistance, please contact the e-mail address given on this datasheet





